

PRODUCT DESCRIPTION

A hand kneadable, specialty epoxy putty that mixes in 1 minute for permanent repairs to many substrates. Contains fading black dye that becomes grey after mixing. May be applied under water (fresh or salt). Bonds to fiberglass, metal, wood, concrete and glass. Will not yellow to UV exposure. Hardens in 10 minutes, back in service in an hour, full strength in 24 hours.

APPLICATIONS

Repairing tanks and drums, patching holes in pipes, stopping leaks and repairing porosity holes in castings.

INSTRUCTIONS FOR USE

Proper surface preparation is essential to a successful application. The following procedures should be considered: Degrease the surface, oil, grease and dirt must be removed before applying any epoxy material.

All surfaces must be thoroughly roughened ideally by grit blasting (8-40 mesh grit), or by grinding with a coarse wheel or abrasive disc pad. An abrasive disc may be used provided white metal is revealed. This creates increased surface area for better adhesion. A 3-5 mil profile is desired for an application. Do not "feather edge" epoxy materials. Epoxy materials must be "locked up" by defined edges and a good 3-5 mil profile. Metal that has been handling sea water or other salt solutions should be grit blasted and high-pressure water blasted and left overnight to allow any salts in the metal to "sweat" to the surface: repeat blasting to "sweat out" all the

soluble salts. A test for chloride contamination should be performed prior to any epoxy application. The maximum soluble salts left on the substrate should be no more than 40p.p.m (parts per million).

Under cold working conditions, heating the repair area to 38°C - 43°C immediately before applying is recommended. This procedure dries off any moisture, contamination or solvents and assists the epoxy in achieving maximum adhesion to the substrate. All prepared surfaces should be repaired as soon as possible, to eliminate any changes or surface contaminants.

Epoxies are very good in water, saturated salt solutions, leaded gasoline, mineral spirits, ASTM # 3 oil and propylene glycol. Epoxies are generally not recommended for long term exposure to concentrated acids and organic solvents. For immersion applications this product is not recommended.

Twist or cut off required amount from stick. Then knead with fingers to a uniform colour. All black colour dye must be gone and a uniform pure grey colour is left. Apply to surface to be repaired within 2 minutes of mixing. The mixed epoxy does not show much bond strength at this time, but can be kneaded or formed into any cracks or holes to be filled.



TECHNICAL FEATURES

Typical Properties	7 days cured at 24°C
Colour	Grey
Viscosity	Putty
Pot Life @24°C	20 mins
Comprehensive Strength	83 N/mm ²
Adhesive Tensile Shear	5 N/mm ²
Cured Hardness Shore D	75
Dielectric Strength volts/mil	300
Solids	100%
Temperature Resistance	121°C Continuous 149°C Intermittent

CHEMICAL RESISTANCE

7 days room temperature cure (30 days immersion)

10% Sulphuric Acid	Fair
10% Hydrochloric Acid	Fair
Chlorinated Solvents	Very Good
Methanol	Very Good
Toluene	Very Good
Ammonia	Very Good
10% Sodium Hydroxide	Excellent
Kerosene	Very Good

HEALTH & SAFETY

This technical information sheet does not constitute a Safety Data Sheet (SDS). Before using this product ensure you have read and fully understood this products SDS

PACKAGING FORMAT

Tube.....50g



PRODUCT DISCLAIMER

BEAL UK offers this Technical Data Sheet ("TDS") for descriptive and informational use only. It is not a warranty, a contract or a substitute for expert or professional advice. Please also see the local product Safety Data Sheet for health and safety considerations. The statements, technical information, data, and recommendations contained in this TDS are provided 'AS IS' and are not warranted or guaranteed in any way. Since the conditions and methods of use of the products are beyond our control, BEAL UK expressly disclaims any and all liability and damages of whatever kind or nature that may arise from any use of the products, the results therefrom, or reliance on the information contained herein. This TDS is one of several tools that may be used to help you find the product best suited for your needs. It is used at your own risk, and by using it, you are knowingly accepting and assuming any and all risks associated with its use and recommendations. BUYERS AND USERS ASSUME ALL RESPONSIBILITY AND LIABILITY FOR ANY AND ALL LOSS OR DAMAGE OF WHATEVER KIND OR NATURE ARISING FROM OR RELATED TO THE HANDLING OR USE OF BEAL'S PRODUCTS. The performance of the product, its shelf life, and application characteristics will depend on many variables, including but not limited to the kind of materials to which the product will be applied, the environment in which the product is stored and/or applied, and the equipment used for the application, among other things. Any change in any of these variables can affect the product's performance. You are responsible to test the suitability of any product in advance for any intended use or application. BEAL UK does not guarantee the reliability, completeness, use, or function of the statements, technical information, data, and recommendations contained in this TDS.

