


TEST REPORT

(Electronic version)



No: 200134230

VERIFICATION WEBSITE: www.gttc.net.cn

VERIFICATION CODE: YHCM-1153-44

扫码下载报告



ISSUE DATE: 2020-06-01

APPLICANT: HAMPOOL ENTERPRISE CO., LIMITED
ADDRESS: ROOM 709, BUILDING B, NO. 399, ZHONGREN RD., JIADING DISTRICT, SHANGHAI, CHINA

INFORMATION CONFIRMED BY APPLICANT:

KN95 MASK

QUANTITY: 60 PIECES

DATE RECEIVED/DATE TEST STARTED: 2020-05-19

CONCLUSION:

FILTRATION EFFICIENCY TO NaCl PARTICULATE MATTER	M
INSPIRATORY RESISTANCE	M
EXPIRATORY RESISTANCE	M
VISUAL FIELD	M
HEAD BAND	M
FLAMMABILITY	M

NOTE: "M" -MEET THE STANDARD'S REQUIREMENT "F" -FAIL TO MEET THE STANDARD'S REQUIREMENT
"—" -NO COMMENT

REMARK:

THIS REPORT IS THE ENGLISH TRANSLATION VERSION OF THE REPORT 200121384.
ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION).
COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.
THE EXPERIMENT WAS CARRIED OUT AT No.1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.

APPROVED BY:

ZiShan Guo SENIOR ENGINEER

郭子山




PAGE 1 OF 4

TEST REPORT

(Electronic version)

No:200134230



TEST REPORT

(Electronic version)

No:200134230

FILTRATION EFFICIENCY TO NaCl PARTICULATE MATTER (%)

(GB 2626-2006 6.3, AIR FLOW:85L/min, AEROSOL:NaCl, AEROSOL CONCENTRATION:15mg/m³, TEMP:23.0℃ RH:35.3%)

FILTRATION EFFICIENCY:

UNTREATED SAMPLE

1# 98.31
2# 98.48
3# 98.66
4# 97.85
5# 98.24
6# 98.80
7# 98.45
8# 97.92
9# 98.14
10# 98.33

CONDITIONING TREATED

1# 96.77
2# 96.95
3# 98.03
4# 96.72
5# 96.90

REQUIREMENT

FILTRATION EFFICIENCY:

≥95.0
(KN95)
(GB 2626-2006)

INSPIRATORY RESISTANCE (Pa)

(GB 2626-2006 6.5, HEAD SIZE: MEDIUM)

UNTREATED SAMPLE:

1# 130.0
2# 127.5

PRETREATMENT SAMPLE:

1# 116.4
2# 119.1

REQUIREMENT

≤350
(GB 2626-2006)

EXPIRATORY RESISTANCE (Pa)

(GB 2626-2006 6.6, HEAD SIZE: MEDIUM)

UNTREATED SAMPLE:

1# 105.0
2# 101.4

PRETREATMENT SAMPLE:

1# 93.7
2# 95.5

REQUIREMENT

≤250
(GB 2626-2006)

VISUAL FIELD (°)

(GB 2890-2009 6.8)

65

REQUIREMENT

≥60
(GB 2626-2006)

HEAD BAND

(GB 2626-2006 6.11)

UNTREATED SAMPLE:

1# PASS

CONDITIONING TREATED:

1# PASS

REQUIREMENT

EACH HEAD BAND, BUCKLE AND OTHER ADJUSTING PARTS OF MASK SHOULD NOT SLIP OR BREAK UNDER 10N TENSION FOR 10S.
(GB 2626-2006)



PAGE 3 OF 4

TEST REPORT

(Electronic version)

No:200134230

FLAMMABILITY(s)

(GB 2626-2006 6.15)

AFTERFLAME TIME
UNTREATED SAMPLE

1# 0.0

2# 0.0

CONDITIONING TREATED

3# 0.0

4# 0.0

REQUIREMENT

AFTERFLAME TIME

≤5

(GB 2626-2006)



————End of Report————

PAGE 4 OF 4